



# POLYCOAT PRODUCTS

A Division of American Polymers Corp.

## POLYCOAT-STAINGARD 1110C

*Aliphatic Polyester  
Polyurethane Topcoat*

### DESCRIPTION

Polycoat-Staingard 1110C is a two component, aliphatic polyester polyurethane for use in moderate to severe chemical environments in indoor or outdoor applications.

### FEATURES

- ❖ Color and Gloss Retention
- ❖ Impact Resistant
- ❖ Chemical Resistance
- ❖ Meets California AQMD Requirements

### TYPICAL USES

- ❖ Concrete
- ❖ Pedestrian Traffic
- ❖ Power Generating Plants
- ❖ Food Processing Facilities
- ❖ Steel Structures & Bridges
- ❖ Milling and Mining Industry
- ❖ Pulp and Paper Industry
- ❖ Plywood
- ❖ Vehicular Traffic
- ❖ Storage Tanks
- ❖ Petrochemical Plants
- ❖ Aircraft Hangars
- ❖ Manufacturing Plants
- ❖ Warehouse Floors

### COLOR

Grey or Clear with a High Gloss finish.

Custom colors are available. Contact Polycoat Products for more information.

### PACKAGING

5 gallon kit (18.9 liter):

Clear Kits: One 5 gallon pail, net fill 2.10 gallons (7.94 liters) of Part-A and one 5 gallon pail, net fill 2.65 gallons (10.01 liters) of Part-B.

Pigmented Kits: One 5 gallon pail, net fill 1.85 gallons (6.7 liters) of Part-A and one 5 gallon pail, net fill 3.15 gallons (11.9 liters) of Part-B.

1 gallon kit (3.78 liter):

Clear Kits: One 1 gallon can, net fill 0.42 gallons (1.59 liters) can containing Part-A and one 1 gallon can, net fill 0.53 gallons (2.00 liters) containing Part-B.

Pigmented Kits: One 1 gallon, net fill 0.37 gallons (1.40 liters) can containing Part-A and one 1 gallon can, net fill 0.63 gallons (2.38 liters) containing Part-B.

### MIXING

Polycoat-Staingard 1110C may not be diluted under any circumstance. Polycoat-Staingard 1110C Part-A and Part-B should be mixed individually before combining. Add Part-B to Part-A while mixing, using a mechanical mixer (Jiffy Mixer) at medium speeds. Mix until a homogeneous mixture and color is obtained (at least 5 minutes) and mix frequently during application to maintain uniform color. Use care to scrape the sides of the container to ensure that no unmixed material remains.

### TECHNICAL DATA

Coverage Rate, per 100 sq. ft. ....	0.5 gal 0.20 l/m <sup>2</sup>
Dry Film Thickness,	
Per coat @ ½ gal. per ft <sup>2</sup> .....	5 ± 2 mils 127 ± 50 mic
Pot Life at 75°F (24°C) .....	60-75 minutes
Flash Point .....	91°F 32.7°C
Total Solids by Volume, ASTM D-2697 .....	69%
Volatile Organic Compounds,	
ASTM D-2369-81 .....	2.08 lbs/gal. 250 gm/liter

### CHEMICAL RESISTANCE (ASTM D-814)

Excellent	Good	Fair	Poor
Distilled Water	Unleaded	Hexanol	IPA, 99%
Skydrol	Gasoline	Acetone	Butanol
Skydrol Jet Fuel		MEK	
Hydraulic oil		MIBK	
Motor Oil		Butyl Acetate	
		Toluene	
		Xylene	

### SURFACE PREPARATION

See General Guidelines for additional surface preparation information.

All surfaces must be free of oil, grease, dirt and other contaminants.

Existing Coatings: A test area should be completed before topcoating.

Concrete: Pressure wash (2-3000 psi) with clean fresh water in conjunction with biodegradable cleanser if necessary to remove all contaminants. Surface shall be dry and free of all oils, wax or any loose sealers or coatings.

Surface temperature should be between 60-100°F (15.5-37.7°C). Do not apply product unless temperature is at least 5° above the dewpoint. Re-coat schedule is 8-48 hours depending on the environment.

### APPLICATION

Check area of application to ensure that it conforms to the substrate requirements as stated in the general guideline section. Prime interior and exterior floors and slabs .

Apply Polycoat-Staingard 1110C Pigmented to the substrate at a rate of ½ gallon/100 sq. ft. (1.9 liters/m<sup>2</sup>). Additional coats may be necessary to achieve desired results.

Polycoat-Staingard 1110C is a high-performance coating and may become slippery when wet.

**Airless Sprayer:** Use Graco 28:1 pump or higher, Binks "Airless" spray gun with Reversa-Clean 0.017-0.019 spray tips and 3/8" solvent resistant fluid line. Adjust pump pressure to the lowest possible setting that provides proper atomization. Equipment of equal performance is acceptable.

**Conventional Spray:** Variations of conventional production spray equipment such as pressure pot, air assisted airless or high volume, low pressure systems as supplied by Binks, Graco, Nordson, Devilbiss or equal may be used.

**Brush:** Use solvent resistant mohair or natural bristle brush with feather edge.

**Roller:** Use solvent resistant phenolic core, short nap sheepskin or equal natural roller covers.

#### **EQUIPMENT CLEANUP**

Equipment should be cleaned environmentally safe solvent, as permitted under local regulations, immediately after use.

#### **STORAGE**

Polycoat-Staingard 1110C has a shelf life of one (1) year from date of manufacture in original, factory sealed containers.

#### **LIMITATIONS**

Polycoat-Staingard 1110C should not be applied in areas where the surface will come into continual contact with water.

The uncured materials used in Polycoat-Staingard 1110C are very sensitive to heat and moisture. Higher temperature and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application. Low temperature and/or low humidity extends the cure time and the use of accelerators may be necessary.

Each application phase to an area should be done in one complete step. A continuous application will ensure a smooth and level coat with no lines or streaks.

Material remaining after application must be tightly sealed to protect it against curing in its container.

#### **WARNING**

This product contains Isocyanates and Solvent.

---

*Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data and instructions.*

#### **LIMITED WARRANTY**

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products current published physical properties. Polycoat Products warrants that its products, when properly installed by a state licensed waterproofing contractor according to Polycoat Products guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of one (1) year. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

#### **DISCLAIMER**

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments.