

## 89 Sta-Tack Primer

**DESCRIPTION:**

Karnak #89 Sta-Tack Primer is a water-based polymer modified primer for self-adhering membranes. Karnak #89 Sta-Tack Primer penetrates pores and dries fast to provide a tacky surface.

**USES:**

Karnak #89 Sta-Tack Primer is designed for use as a primer prior to the installation of self-adhering membranes. This thin solution readily penetrates pores and dries fast to provide a tacky, firm substrate for adhesion of the membranes. Karnak #89 Sta-Tack Primer is suitable for use over asphalt, wood, plywood, gypsum board and concrete surfaces.

**ADVANTAGES:**

1. Easy to apply
2. Quick Drying
3. Promotes adhesion
4. Use as is, needs no intermixing
5. VOC Compliant

**SURFACE PREPARATION:**

All surfaces should be clean, dry and free from oil, grease, dust, dirt, loose paint or other foreign matter.

**APPLICATION:**

Easily applied by brush, roller or hand sprayer at the rate of 0.20 (1/5<sup>th</sup> gallon) gallon per 100 sq. ft. (500 sq. ft. per gallon)

**COVERAGE RATE:**

Apply at the rate of 0.20 gallon per 100 sq. ft.

**CARE OF TOOLS:**

Uncured material may be cleaned with water. Cured material may be cleaned with Karna-Klean, mineral spirits or similar solvent.

**CAUTION:**

Do not apply when rain is imminent. Protect from freezing. Primer must be dried before exposure to water. Store between 50°F and 100°F. Keep container covered when not in use. Do not thin. Keep out of reach of children. Do not take internally. Harmful if swallowed. Avoid contact with eyes and skin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying.

**KARNAK**

Distributed by: BEST MATERIALS LLC  
Ph: 800-474-7570, 602-272-8128  
Email: [sales@bestmaterials.com](mailto:sales@bestmaterials.com)  
[www.bestmaterials.com](http://www.bestmaterials.com)

## 86 Sta-Tack Primer

**PACKAGING:**

Available in 1 gallon cans and 5 gallon pails.

**PHYSICAL PROPERTIES:**

Weight Per Gallon:	8.61 lbs.
Solid By Weight:	37%
Color:	Blue
Dry Time:	30 Minutes @ 77°F and 50% RH
Cure Time:	2 Hours @ 77°F and 50% RH
Application Temp:	40°F and Rising
Service Temp:	-40°F to 160°F
Coverage:	0.20 gal. per 100 sq. ft.
VOC's:	50 gm/L

Distributed by: BEST MATERIALS LLC  
Ph: 800-474-7570, 602-272-8128  
Email: [sales@bestmaterials.com](mailto:sales@bestmaterials.com)  
[www.bestmaterials.com](http://www.bestmaterials.com)

**KARNAK**